

Express Mail Label No. EL209599882US
U.S. National Phase Entry of PCT/EP00/09882
"Interface Module for a Local Data Network"
Filed: 18 January 2002
PRELIMINARY AMENDMENT

3. (Amended) The interface module according to claim 1, wherein the alloy has the composition $\text{Co}_a(\text{Fe}_{1-c}\text{Mn}_c)_b\text{Ni}_d\text{M}_e\text{Si}_x\text{B}_y\text{C}_z$, with M indicating one or more elements from the group Nb, Mo, Ta, Cr, W, Ge, and/or P and $a+b+d+e+x+y+z = 100$, with

Co $a = 40 - 82 \text{ at\%}$

Fe+Mn $b = 3 - 10 \text{ at\%}$

Mn/Fe $c = 0 - 1$

Ni $d = 0 - 30 \text{ at\%}$

M $e = 0 - 5 \text{ at\%}$

Si $x = 0 - 17 \text{ at\%}$

B $y = 8 - 26 \text{ at\%}$

C $z = 0 - 3 \text{ at\%}$

and $15 \text{ at\%} < e+x+y+z < 30 \text{ at\%}$.

4. (Amended) The interface module according to claim 3, wherein the following relationships apply:

Co $a = 55 - 72 \text{ at\%}$

Mn/Fe $c = 0 - 0.5$

Ni $d = 0 - 20 \text{ at\%}$

M $e = 0 - 3 \text{ at\%}$

B $y = 8 - 20 \text{ at\%}$

Si $x = 1 - 18 \text{ at\%}$

Express Mail Label No. EL209599882US
U.S. National Phase Entry of PCT/EP00/09882
"Interface Module for a Local Data Network"
Filed: 18 January 2002
PRELIMINARY AMENDMENT

and $20 \text{ at\%} < e+x+y+z < 30 \text{ at\%}$.

5. (Amended) The interface module according to claim 1, wherein the alloy has the composition $\text{Fe}_x\text{Cu}_y\text{M}_z\text{Si}_v\text{B}_w$, with M indicating an element from the group Nb, W, Ta, Zr, Hf, Ti, Mo, or a combination of these and $x + y + z + v + w = 100\%$, with

Fe $x = 100\% - y - z - v - w$

Cu $y = 0.5 - 2 \text{ at\%}$

M $z = 1 - 6 \text{ at\%}$

Si $v = 6.5 - 18 \text{ at\%}$

B $w = 5 - 14 \text{ at\%}$

with $v + w > 18 \text{ at\%}$.

6. (Amended) The interface module according to claim 5, wherein the following relationships apply:

Cu $y = 1 \text{ at\%}$

M $z = 2 - 4 \text{ at\%}$

Si $v = 14 - 17 \text{ at\%}$,

with $v + w = 20 \text{ to } 24 \text{ at\%}$.

7. (Amended) The interface module according to claim 1, wherein the alloy has the composition $\text{Fe}_x\text{Zr}_y\text{Nb}_z\text{B}_v\text{Cu}_w$, with $x + y + z + v + w = 100 \text{ at\%}$, with

Express Mail Label No. EL209599882US
U.S. National Phase Entry of PCT/EP00/09882
"Interface Module for a Local Data Network"
Filed: 18 January 2002
PRELIMINARY AMENDMENT

Fe $x = 100 \text{ at\%} - y - z - v - w$

Zr $y = 2 - 5 \text{ at\%}$

Nb $z = 2 - 5 \text{ at\%}$

B $v = 5 - 9 \text{ at\%}$

Cu $w = 0.5 - 1.5 \text{ at\%}$

with $y + z > 5 \text{ at\%}$ and $y + z + v > 11 \text{ at\%}$.

8. (Amended) The interface module according to claim 7, wherein the following relationships apply:

Fe $x = 83 - 86 \text{ at\%}$

Zr $y = 3 - 4 \text{ at\%}$

Nb $z = 3 - 4 \text{ at\%}$

Cu $w = 1 \text{ at\%}$

with $y + z > 7 \text{ at\%}$ and $y + z + v > 12 \text{ to } 16 \text{ at\%}$.

9. (Amended) The interface module according to claim 1, wherein the alloy has the composition $\text{Fe}_x\text{M}_y\text{B}_z\text{Cu}_w$, with M indicating an element from the group Zr, Hf, Nb and $x + y + z + w = 100 \text{ at\%}$, with

Fe $x = 100 \text{ at\%} - y - z - w$

M $y = 6 - 8 \text{ at\%}$

B $z = 3 - 9 \text{ at\%}$

Express Mail Label No. EL209599882US
U.S. National Phase Entry of PCT/EP00/09882
"Interface Module for a Local Data Network"
Filed: 18 January 2002
PRELIMINARY AMENDMENT

Cu $w = 0 - 1.5 \text{ at\%}$.

10. (Amended) The interface module according to claim 9, wherein the following relationships apply:

Fe $x = 83 - 91 \text{ at\%}$

M $y = 7 \text{ at\%}$.

11. (Amended) The interface module according to claim 1, wherein the alloy has the composition $(\text{Fe}_{0.98}\text{Co}_{0.02})_{90-x}\text{Zr}_7\text{B}_{2+x}\text{Cu}_1$, with $x = 0 - 3 \text{ at\%}$, with the residual alloy component Co able to be replaced by Ni with appropriate equalization.

12. (Amended) The interface module according to claim 11, wherein $x = 0$.

13. (New) The interface module according to claim 2, wherein the alloy has the composition $\text{Co}_a(\text{Fe}_{1-c}\text{Mn}_c)_b\text{Ni}_d\text{M}_e\text{Si}_x\text{B}_y\text{C}_z$, with M indicating one or more elements from the group Nb, Mo, Ta, Cr, W, Ge, and/or P and $a+b+d+e+x+y+z = 100$, with

Co $a = 40 - 82 \text{ at\%}$

Fe+Mn $b = 3 - 10 \text{ at\%}$

Mn/Fe $c = 0 - 1$

Ni $d = 0 - 30 \text{ at\%}$

M $e = 0 - 5 \text{ at\%}$

Express Mail Label No. EL209599882US
U.S. National Phase Entry of PCT/EP00/09882
"Interface Module for a Local Data Network"
Filed: 18 January 2002
PRELIMINARY AMENDMENT

Si $x = 0 - 17 \text{ at\%}$

B $y = 8 - 26 \text{ at\%}$

C $z = 0 - 3 \text{ at\%}$

and $15 \text{ at\%} < e+x+y+z < 30 \text{ at\%}$.

14. (New) The interface module according to claim 2, wherein the alloy has the composition $\text{Fe}_x\text{Cu}_y\text{M}_z\text{Si}_v\text{B}_w$, with M indicating an element from the group Nb, W, Ta, Zr, Hf, Ti, Mo, or a combination of these and $x + y + z + v + w = 100\%$, with

Fe $x = 100\% - y - z - v - w$

Cu $y = 0.5 - 2 \text{ at\%}$

M $z = 1 - 6 \text{ at\%}$

Si $v = 6.5 - 18 \text{ at\%}$

B $w = 5 - 14 \text{ at\%}$

with $v + w > 18 \text{ at\%}$.

15. (New) The interface module according to claim 2, wherein the alloy has the composition $\text{Fe}_x\text{Zr}_y\text{Nb}_z\text{B}_v\text{Cu}_w$, with $x + y + z + v + w = 100 \text{ at\%}$, with

Fe $x = 100 \text{ at\%} - y - z - v - w$

Zr $y = 2 - 5 \text{ at\%}$

Nb $z = 2 - 5 \text{ at\%}$

B $v = 5 - 9 \text{ at\%}$

Express Mail Label No. EL209599882US
U.S. National Phase Entry of PCT/EP00/09882
"Interface Module for a Local Data Network"
Filed: 18 January 2002
PRELIMINARY AMENDMENT

Cu $w = 0.5 - 1.5 \text{ at\%}$

with $y + z > 5 \text{ at\%}$ and $y + z + v > 11 \text{ at\%}$.

16. (New) The interface module according to claim 2, wherein the alloy has the composition $\text{Fe}_x\text{M}_y\text{B}_z\text{Cu}_w$, with M indicating an element from the group Zr, Hf, Nb and $x + y + z + w = 100 \text{ at\%}$, with

Fe $x = 100 \text{ at\%} - y - z - w$

M $y = 6 - 8 \text{ at\%}$

B $z = 3 - 9 \text{ at\%}$

Cu $w = 0 - 1.5 \text{ at\%}$.

17. (New) The interface module according to claim 2, wherein the alloy has the composition $(\text{Fe}_{0.98}\text{Co}_{0.02})_{90-x}\text{Zr}_7\text{B}_{2+x}\text{Cu}_1$, with $x = 0 - 3 \text{ at\%}$, with the residual alloy component Co able to be replaced by Ni with appropriate equalization.

Respectfully submitted



Dean W. Russell
Reg. No. 33,452

KILPATRICK STOCKTON LLP
1100 Peachtree Street, Suite 2800
Atlanta, Georgia 30309
(404) 815-6528